

ESSENTIAL R5855

FORMULATED HIGH GLOSS ACRYLIC EMULSION

DESCRIPTION

Essential R5855 is a high gloss, acrylic polymer. It is intended for clear or lightly pigmented coatings and stains for wood, metal and plastic surfaces. R5855 contains coalescing, leveling and defoaming agents making it a fully formulated, clear, water-based product. This product may be thinned with water and forms an excellent high gloss finish suitable for floor finishes and wood stock, cabinets and trim, as well as plastic and metal coatings. It is non-yellowing and can be recoated in 30-60 minutes.

R5855 forms a hard, stain-resistant film with exceptional clarity and mar resistance. It exhibits superior flow and leveling properties and is self-cross-linking to produce fast-drying films.

KEY BENEFITS

- Very Clear Film
- Formulation Versatility (Sealers and Topcoats)
- Fast-Drying
- Ready-To-Use

TYPICAL PROPERTIES*

Appearance	Milky-White Emulsion
pH	7.8
Solids, % by Weight	31.0
Solids, % by Volume	26.0
Viscosity, cP @ 25°C	150
Density, Lbs./Gal.	8.8
VOC Level (As Supplied)	
Lbs./Gal.	2.15
G/L	258
Freeze/Thaw Stable	Passes 3 Cycles

**These values should not be interpreted as specifications.*

Visit us on the web at www.essentialrmd.com

*DISCLAIMER: The information and recommendations contained herein are based on data believed to be correct. The information is offered solely for the customer's consideration, investigation and verification because of numerous factors beyond our control affecting the results of the use of products, Essential Industries, INC. makes no warranty of any kind, expressed or implied, including those of merchantability and fitness for a particular purpose, other than that the product conforms to its applicable current standard specification. The manufacturer's only obligation shall be to replace such quantity of the product proven to be defective.

F0409

ESSENTIAL R5855

TYPICAL FILM PROPERTIES

Air Dry (23% Solids at 0.2 Mils)

Tack-Free

Hard

Recoat

Konig Hardness (Seconds)

Flexibility

Humidity Resistance

(Relative Humidity at 100%)

Water Soak Resistance

Intercoat Adhesion

Recoatability

5 Minutes

20 Minutes

30 Minutes

127

1/4 Mandrel, Pass

(Cold Rolled Steel, Bonderite 1000)

Excellent (Passes 240 Hrs., 100°F)

Excellent (Passes 240 Hrs., 100°F)

Excellent

Excellent